

Tolérances des barres laminées à chaud Toleranzen Stabstahl warmgewalzt

● EN 10060 (DIN 1013)

Gamme de dimension Abmessungsbereich mm	Tolérances Toleranzen mm
10-15	+/-0.4
16-25	+/-0.5
26-35	+/-0.6
36-50	+/-0.8
52-80	+/-1.0
85-100	+/-1.3
105-120	+/-1.5
125-160	+/-2.0
165-200	+/-2.5
220	+/-3.0
250	+/-4.0

■ EN 10059 (DIN 1014)

Gamme de dimension Abmessungsbereich mm	Tolérances Toleranzen mm
8-14	+/-0.4
15-25	+/-0.5
26-35	+/-0.6
40-50	+/-0.8
55-90	+/-1.0
100	+/-1.3
110-120	+/-1.5
130-150	+/-1.8

— EN 10058 (DIN 1017)

Gamme de dimension Abmessungsbereich Epaisseur / Dicke mm	Tolérances Toleranzen mm
5-20	+/-0.5
22-40	+/-1.0
42-80	+/-1.5
Largeur Breite mm	Tolérances Toleranzen mm
10-35	+/-0.75
40-75	+/-1.0
80-100	+/-1.5
105-120	+/-2.0
125-150	+/-2.5